

IN THE CLAIMS:

Please cancel claims 12-16 and 30 without prejudice and amend the claims as follows:

1. (Original) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosiloxanes selected from the group consisting of 1,3-dimethyldisiloxane, 1,1,3,3-tetramethyldisiloxane, hexamethyldisiloxane, 1,3-bis(silanomethylene)disiloxane, bis(1-methyldisiloxanyl)methane, 2,2-bis(1-methyldisiloxanyl)propane, 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, 1,3,5,7,9-pentamethylcyclopentasiloxane, 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene, 1,3,5-trisilanetetrahydropyran, and 2,5-disilanetetrahydrofuran while applying RF power, wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.
2. (Original) The method of claim 1, wherein at least one of the organosiloxanes is cyclic and comprises C, H, and O.
3. (Original) The method of claim 2, wherein the cyclic organosiloxane comprising C, H, and O is 1,3,5,7-tetramethylcyclotetrasiloxane.
4. (Original) The method of claim 1, wherein the two or more organosiloxanes are reacted with an oxidizing gas.
5. (Original) The method of claim 4, wherein the oxidizing gas is selected from the group consisting of oxygen, ozone, nitrous oxide, carbon dioxide, and water.
6. (Original) The method of claim 1, wherein the RF power is pulsed to increase the porosity of the film.

7. (Original) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosiloxanes selected from the group consisting of 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, 1,3,5,7,9-pentamethylcyclopentasiloxane, 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene, 1,3,5-trisilanetetrahydropyran, and 2,5-disilanetetrahydrofuran while applying RF power, wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.

8. (Currently Amended) The method of claim 7, wherein at least one of the organosiloxanes is selected from the group consisting of 1,3,5-trisilanetetrahydropyran[[,]] and 2,5-disilanetetrahydrofuran.

9. (Original) The method of claim 7, wherein the two or more organosiloxanes are reacted with an oxidizing gas while applying RF power.

10. (Original) The method of claim 9, wherein the oxidizing gas is selected from the group consisting of oxygen, ozone, nitrous oxide, carbon dioxide, and water.

11. (Original) The method of claim 7, wherein the RF power is pulsed to increase the porosity of the film.

12-16. (Canceled)

17. (Original) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosiloxanes, wherein a first organosiloxane of the two or more organosiloxanes is cyclic and comprises C, H, and O and a ring comprising carbon and oxygen, and a second organosiloxane of the two or more organosiloxanes is selected from the group consisting of 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, and 1,3,5,7,9-pentamethylcyclopentasiloxane, while applying RF power, wherein the low dielectric


constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.

18. (Original) The method of claim 17, wherein the first organosiloxane is selected from the group consisting of 1,3,5-trisilanetetrahydropyran, 2,5-disilanetetrahydrofuran, and 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene.

19. (Original) The method of claim 18, wherein the first organosiloxane is 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene.

20. (Original) The method of claim 17, wherein the two or more organosiloxanes are reacted with an oxidizing gas.

21. (Previously Presented) A method for depositing a low dielectric constant film on a substrate, comprising plasma assisted reaction of a mixture comprising an oxidizing gas and a siloxane comprising



wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.

22. (Previously Presented) The method of claim 21, wherein the mixture further comprises a siloxane selected from the group consisting of 1,3-dimethyldisiloxane, 1,1,3,3-tetramethyldisiloxane, 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, 1,3,5,7,9-pentamethylcyclopentasiloxane, bis(1-methyldisiloxanyl)-methane, 2,2-bis(1-methyldisiloxanyl)propane, and 2,5-disilanetetrahydrofuran.

23. (Previously Presented) The method of claim 21, wherein the siloxane is selected from the group consisting of 1,3-bis(silanomethylene)disiloxane, 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene, and 1,3,5-trisilanetetrahydropyran.

24. (Previously Presented) The method of claim 21, wherein the siloxane is 1,3-bis(silanomethylene)disiloxane.
25. (Previously Presented) The method of claim 24, wherein the oxidizing gas is N_2O .
26. (Previously Presented) The method of claim 21, wherein the mixture further comprises an inert gas.
27. (Previously Presented) The method of claim 21, wherein the plasma is formed by RF power comprising high frequency RF power.
28. (Previously Presented) The method of claim 27, wherein the high frequency RF power is pulsed.
29. (Previously Presented) The method of claim 1, wherein the reacting the two or more organosiloxanes comprises reacting the two or more organosiloxanes with N_2O in the presence of a gas selected from the group consisting of He, Ar, Ne, and nitrogen.
30. (Canceled)
31. (Previously Presented) The method of claim 17, wherein the reacting the two or more organosiloxanes comprises reacting the two or more organosiloxanes with N_2O in the presence of a gas selected from the group consisting of He, Ar, Ne, and nitrogen.